

**This Page Is Inserted by IFW Operations
and is not a part of the Official Record**

BEST AVAILABLE IMAGES

**Defective images within this document are accurate representations of
the original documents submitted by the applicant.**

Defects in the images may include (but are not limited to):

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 07003471
PUBLICATION DATE : 06-01-95


APPLICATION DATE : 22-06-93
APPLICATION NUMBER : 05150624

APPLICANT : KAO CORP;

INVENTOR : YAMAMOTO YUZO;

INT.CL. : C23C 28/00 B32B 15/08 C23C 22/00
C25D 5/26 C25D 11/38 C25D 15/02

TITLE : COMPOSITE PLATED STEEL SHEET



ABSTRACT : PURPOSE: To obtain a composite plated steel sheet combining excellent pitting corrosion resistance, coating finishing characteristics, and coating adhesion by providing Zn-Ni plating layers of specific composition and Zn-Ni-(water-soluble high polymer) composite plating layers to both sides of a steel sheet, respectively, and further providing a chromate film layer and an organic resin film layer to one side of the steel sheet.

CONSTITUTION: Zn-Ni plating layers 2, containing $\geq 25\text{wt.}\%$ Ni and having (1 to 1000) mg/m^2 plating weight, are provided to both sides of a steel sheet 1. Then, Zn-Ni-(water-soluble high polymer) composite plating layers 4, containing 5-16% Ni and 0.01-30% water-soluble high polymer and having (10 to 60) g/m^2 plating weight, are provided to the above plating layers. It is preferable to use, as the water-soluble high polymer, an anionic, cationic, or amphoteric organic high polymer having 1,000 to 1,000,000 weight average molecular weight and containing specific aromatic ring, hydroxyl group, sulfone group, etc. Further, a chromate film layer 5 of (10 to 150) mg/m^2 plating weight, expressed in terms of Cr, is provided to at least one surface, and then, an organic resin film layer 6 of 0.3-3 μm thickness is provided on this layer.

COPYRIGHT: (C)1995,JPO